



BESTON GROUP CO., LTD

9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER, ZHENGZHOU CITY, CHINA

WEB: www.bestongroup.com

裂解实验单/Pyrolysis Test

日期/Date: 2024/12/28

送样人/Sender: Ms. Wen

样品资料/Sample information:			
样品名称 Name	HDPE plastic granules	送样重量 Weight	/
样品状态 Sample status	/	取样重量 Sampling weight	180g
实验用时 Time	2h 33min	实验温度 Temperature	306°C
实验过程/Testing progress:			
序号 No.	时间段 Time	烟气温度 Flue gas temperature	备注 Remark
1	8:45	16°C	开始加热 Start heating
2	9:31	229°C	开始出油 Oil production starts
3	9:42	246°C	出油加快 Oil production increases
4	9:50	300°C	/
5	10:13	306°C	/
6	10:50	258°C	出油减慢 Oil production decreases
7	11:18	217°C	停止加热 Stop heating
实验结果/Result:			
项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%
裂解试验 Pyrolysis testing	油 Oil	158.5g	88.06%
	渣 Residue	2.5g	1.39%
	气 Gas	19g	10.56%
实验总结 Test summary			
备注: 以上数据仅供参考 Noted: The above data is for reference only		签章/signature:	



BESTON GROUP CO., LTD

9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER, ZHENGZHOU CITY, CHINA

WEB: www.bestongroup.com

原料图片 Raw Material



油样图片 Oil Product



渣样图片 Solid Residue

